

**ACOUSTI-MATE™**  
**Melting, Discoloring & Flashpoints**

<u>MATERIAL</u>	<u>Melting Point</u>	<u>Discoloring Point</u>	<u>Flash Point</u>
ALUMINUM	950°f – 1220°f	400°f	NA
T304 STAINLESS STEEL	2550°f – 2650°f	400°f	NA
T316 STAINLESS STEEL	2500°f – 2550°f	400°f	NA
KRAFT MOISTURE BARRIER	212°f	NA	450°f
POLYSURLYN MOISTURE BARRIER	207°f	NA	400°f